

Concrete Mixture Analysis Worksheet

Project Name: Miscellaneous Mix Designs
 Client Name: Daytona Redi Mix
 MDOT Project #: Various
 Maximum Aggregate Size (inches): 1.5

Date: 5/14/2024
 CT Project #: 230408
 Mix ID #: 3500HP (Slag - Mid-Range)

MATERIALS				
Type	Source	Class	Spec. Grav.	F/T Dialation
Coarse	Manitoulin (MDOT 95-0005CA)	6AA	2.82	0.001
Intermediate	Port Inland (MDOT 74-0005CA)	26A	2.68	0.036
			1.00	
Fine	Krake-Measel (MDOT 44-0051SG)	2NS	2.68	
Cement	Ash Grove - Missisauga	Type IL	3.10	
GGBFS	Ash Grove - Detroit	100	2.91	
ADMIXTURES				
Type	Supplier	Dosage (oz/cwt)		
SA-50	MAPEI	0.8		
Dynamon SX	MAPEI	5		

PROPORTIONS (SSD)				
Type	Wt. lbs.	Sp. Grav.	Vol. ft ³	% Vol.
Cement	395	3.1	2.04	
GGBFS	131	2.91	0.72	
Coarse	1645	2.82	9.35	49.66
Intermediate	300	2.68	1.79	9.53
		1.00	0.00	0.00
Fine	1285	2.68	7.68	40.82
27.05				
Water	231	1	3.70	
Air, %	6.5		1.76	
Total Cementitious:		526	lbs. or	5.6 bag
Water/Cement Ratio:		0.44		
Percent Cementitious Replacement:		25%		

	GRADATIONS								Gradation Date: <u>5/17/2024</u>			
	Coarse		Intermediate		0		Fine					
	SSD wt., lbs	1645	300	0	1285					Total % Passing	% Cumm. Retained	Retained Sieve, %
Abs. Volume	9.35	1.79	0.00	7.68								
Aggregate % Vol.	49.7	9.5	0.0	40.8								
Sieves	% Pass	% Mix	% Pass	% Mix	% Pass	% Mix	% Pass	% Mix				
2"	100	49.7	100	9.5	0.0	0.0	100	40.8	100.0	0.0	0.0	
1 1/2"	100	49.5	100	9.5	0.0	0.0	100	40.8	99.8	0.2	0.2	
1"	100	49.7	100	9.5	0.0	0.0	100	40.8	100.0	0.0	-0.2	
3/4"	82	40.7	100	9.5	0.0	0.0	100	40.8	91.1	8.9	8.9	
1/2"	47	23.3	97	9.2	0.0	0.0	100	40.8	73.4	26.6	17.7	
3/8"	21	10.4	83	7.9	0.0	0.0	100	40.8	59.2	40.8	14.2	
# 4	4	2.0	16	1.5	0.0	0.0	99	40.4	43.9	56.1	15.2	
# 8	3	1.5	5	0.5	0.0	0.0	84	34.3	36.3	63.7	7.7	
# 16	3	1.5	3	0.3	0.0	0.0	68	27.8	29.5	70.5	6.7	
# 30	2	1.0	2	0.2	0.0	0.0	53	21.6	22.8	77.2	6.7	
# 50	2	1.0	2	0.2	0.0	0.0	25	10.2	11.4	88.6	11.4	
# 100	2	1.0	2	0.2	0.0	0.0	5	2.0	3.2	96.8	8.2	
# 200	2	0.8	2	0.2	0.0	0.0	1	0.4	1.4	98.6	1.9	

Fine Aggregate Fineness Modulus: 2.66 FM

Coarseness Factor (x-axis): 64
((cumm. Ret 3/8 / cumm. Ret #8) x 100)

Workability Factor (y-axis): 36
(Pass #8 + Adjustment Factor)

